

Precision Steel

# precidur<sup>®</sup> DD11

Product information for hot-rolled precision strip made in Hohenlimburg



thyssenkrupp

Version 9/21

## Mild, unalloyed steel

Mild, unalloyed steels are supplied in accordance with DIN EN 10111. The BU Precision Steel supplies hot-rolled strip with very low earing for the deep drawing of sleeves and similar components.

Beyond the standard grades we also offer a wide variety of special grades optimized for different purpose.

---

## Contents

Brief portrait  
Technical features  
Chemical composition  
Mechanical properties  
General thickness tolerances  
Delivery options  
Application examples

---

## precidur<sup>®</sup>

- is used in virtually all industry sectors.
- offers close thickness tolerances similar to cold-rolled strip, optimum surface finishes and consistent material properties over the entire strip length and width.
- is characterized by its symmetrical strip profiles and mill edges.
- is the sum of all the experience we have gained in more than 100 years of manufacturing and processing steel.

## Technical features

Mild, unalloyed steel

Material number:	1.0332
Material name:	DD11
Proprietary brand:	precidur® DD11
Old name:	STW 22
Delivery specification:	DIN EN 10111
Application:	Mild unalloyed steel for cold forming

### Chemical composition

Ladle analysis mass percentages	C [%]	Si [%]	Mn [%]	P [%]	S [%]	Al [%]
min.	-	-	-	-	-	0.015
max.	0.12	0.04	0.50	0.025	0.015	0.070

Further special analyses available

### Mechanical properties

Longitudinal to rolling direction	Yield strength R <sub>eL</sub> [MPa]	Tensile strength R <sub>m</sub> [MPa]	Elongation A <sub>5</sub> [%]	A <sub>80</sub> [%]
Rolled condition*	170 - 340	max. 440	min. 28	min. 24

\* Restricted mechanical property ranges and specific processing properties can be agreed on request.

### Possible delivery options

Options	Mill edge (NK) Cut edge (GK)	pickled	unpickled	slit	trimmed	Cut to length
precidur® DD11	NK or GK	✓	or ✓	✓	✓	✓

### General thickness tolerances

Strip thickness [mm]	1.5 – 2.54	2.55 – 4.03	4.04 – 6.03	6.04 – 8.03	8.04 – 9.03	9.04 – 11.03	11.04 – 14.03	14.04 – 16.00
Standard tolerances [mm]	± 0.04	± 0.04	± 0.05	± 0.055	± 0.06	± 0.07	± 0.08	± 0.10
Special tolerances [mm]	± 0.03	± 0.035	± 0.04	± 0.045	± 0.05	± 0.055	± 0.06	± 0.07

### General delivery options

Coil inner diameter:	standard 508 mm / optional 610 mm
Coil outer diameter:	max. 1,890 mm
Coil weight:	max. 20.5 kg/mm strip width
Strip width*:	max. 720 mm
Strip thickness*:	1.5 – 16 mm

\* May be subjected to restrictions.

## Application examples for mild, unalloyed steels



Special mill grades feature unique thyssenkrupp properties. Other terms and conditions of supply not specified here will be based on the applicable specifications. The specifications used will be those valid on the date of publication of this product information.

### General information:

All statements as to the properties or utilization of material and products are for the purpose of description only. Guarantees in respect of the existence of certain properties or utilization are only valid if agreed in writing. Subject to technical changes. Reprints, in whole or in part, only with the permission of thyssenkrupp Hohenlimburg GmbH. The latest version of this product information can be found at: <https://www.thyssenkrupp-steel.com/en/publications/>

Please contact our sales/technical customer support team for detailed information.

thyssenkrupp Hohenlimburg GmbH, Oeger Str. 120, 58119 Hagen  
T: +49 2334 91 2555  
[www.thyssenkrupp-steel.com](http://www.thyssenkrupp-steel.com), [info.precisionsteel@thyssenkrupp.com](mailto:info.precisionsteel@thyssenkrupp.com)