

Precision Steel

# precidur<sup>®</sup> HSM 420 HD / S420MC

Product information for hot-rolled precision strip made in Hohenlimburg



thyssenkrupp

Version 11/24

## Microalloyed fine grain structural steel high ductility (HD)

High ductility (HD) microalloyed fine grain structural steels from BU Precision Steel meet the specifications of DIN EN 10149. They are produced with a very fine microstructure and embedded nano-precipitates. These steel grades open up new design options in lightweight auto construction. Their extremely low carbon content counters the formation of coarse and brittle areas in the microstructure.

These materials are particularly suitable for the manufacture of complex forming geometries. Compared with conventional microalloyed steels they offer higher shear strain values and multiaxial elongation for greater process reliability in component production and are readily weldable.

## Contents

Brief portrait  
Technical features  
Chemical composition  
Mechanical properties  
General thickness tolerances  
Delivery options  
Application examples

### precidur<sup>®</sup>

- is used in virtually all industry sectors.
- offers close thickness tolerances similar to cold-rolled strip, optimum surface finishes and consistent material properties over the entire strip length and width.
- is characterized by its symmetrical strip profiles and mill edges.
- is the sum of all the experience we have gained in more than 100 years of manufacturing and processing steel.

engineering.tomorrow.together.

## Technical features

Microalloyed fine grain structural steel High ductility (HD)

Material number: 1.0980

Material name: S420MC / H420LA

Proprietary brand: precidur® HSM 420 HD

Delivery specification: DIN EN 10149-2 / VDA 239-100

Application: Steels with very good forming, fine blanking and welding properties

Special feature: An adapted and optimized chemical analysis combined with a specially designed hot rolling strategy creates a ferritic microstructure with nano-precipitates. This results in increased forming reserves compared with the standard variant S420MC.

### Chemical composition

Ladle analysis mass percentages	C [%]	Si [%]	Mn [%]*	P [%]	S [%]	Al [%]	Ti [%]	Nb [%]	V [%]
min.	-	-	-	-	-	0.015	-	-	-
max.	0.04	0.10	0.40	0.020	0.008	0.060	0.05	0.08	0.05

Further special analyses available

\* Chemical analysis suitable for scrap melting, Mn = max. 0.3%

### Mechanical properties

Longitudinal to rolling direction	Yield strength R <sub>eH</sub> [MPa]	Tensile strength R <sub>m</sub> [MPa]	Elongation A <sub>5</sub> [%]	A <sub>80</sub> [%]
Rolled condition	min. 420	480 - 580	min. 24	min. 19

### Possible delivery options

Options	Mill edge (NK) Cut edge (GK)	pickled	unpickled	slit	trimmed	Cut to length
precidur® HSM 420 HD	NK or GK	✓	or ✓	✓	✓	✓

### General thickness tolerances

Strip thickness [mm]	1.5 – 2.54	2.55 – 4.03	4.04 – 6.03	6.04 – 8.03	8.04 – 9.03	9.04 – 11.03	11.04 – 14.03	14.04 – 16.00
Standard tolerances [mm]	± 0.04	± 0.04	± 0.05	± 0.055	± 0.06	± 0.07	± 0.08	± 0.10
Special tolerances [mm]	± 0.03	± 0.035	± 0.04	± 0.045	± 0.05	± 0.055	± 0.06	± 0.07

### General delivery options

Coil inner diameter: standard 508 mm / optional 610 mm

Coil outer diameter: max. 1,890 mm

Coil weight: max. 20.5 kg/mm strip width

Strip width\*: max. 720 mm

Strip thickness\*: 1.5 – 16 mm

\* May be subjected to restrictions.

## Application examples for microalloyed fine grain structural steel high ductility (HD)



Special mill grades feature unique thyssenkrupp properties. Other terms and conditions of supply not specified here will be based on the applicable specifications. The specifications used will be those valid on the date of publication of this product information.

Please contact our sales/technical customer support team for detailed information.

thyssenkrupp Hohenlimburg GmbH, Oeger Str. 120, 58119 Hagen  
T: +49 2334 91 0  
[www.thyssenkrupp-steel.com](http://www.thyssenkrupp-steel.com), [info.precisionsteel@thyssenkrupp-steel.com](mailto:info.precisionsteel@thyssenkrupp-steel.com)

### General information:

All statements as to the properties or utilization of material and products are for the purpose of description only. Guarantees in respect of the existence of certain properties or utilization are only valid if agreed in writing. Subject to technical changes. Reprints, in whole or in part, only with the permission of thyssenkrupp Hohenlimburg GmbH. The latest version of this product information can be found at: <https://www.thyssenkrupp-steel.com/en/publications/>