

C67/C67S

Product information for hot-rolled precision strip



thyssenkrupp

Version 1/18

Heat treatable and spring steel

Whether it's for wear parts, springs, chain links or safety components, heat treatable steels from BU Precision Steel offer the right solution for all requirements. Good fine blanking properties and formability in the annealed condition are combined with high strengths and good toughness in the quenched and tempered condition. Close analysis ranges tailored to specific purposes and precisely controlled rolling parameters guarantee consistent and outstanding processability and consistent heat treatment results.

We can supply a variety of unalloyed and alloyed heat treatable steels in accordance with DIN EN 10083 with carbon contents between 0.20% and 0.60%, and spring steels in accordance with DIN EN 10132-4.

Hohenlimburg precision strip:

- is used in virtually all industry sectors.
- offers close thickness tolerances similar to cold-rolled strip, optimum surface finishes and consistent material properties over the entire strip length and width.
- is characterized by its symmetrical strip profiles and mill edges.
- is the sum of all the experience we have gained in more than 100 years of manufacturing and processing steel.

Contents

Brief portrait
Technical features
Chemical composition
Mechanical properties
General thickness tolerances
Delivery options
Application examples

Technical features

Heat treatable steel

Material number: 1.0603 / 1.1231

Material name: C 67 / C 67 S

Delivery specification: analogous to DIN EN 10132-4

Application: Spring steel

Chemical composition

Ladle analysis mass percentages	C [%]	Si [%]	Mn [%]	P [%]	S [%]	Cr [%]	Mo [%]	Ni [%]	Al [%]	Cu [%]
min.	0.66	0.15	0.60	–	–	0.10	–	–	–	–
max.	0.73	0.35	0.90	0.025	0.015	0.40*	0.10	0.20	0.015	0.20

Further special analyses available * Cr-free variant available

Mechanical properties

Longitudinal to rolling direction	Tensile strength R_m [MPa]	Elongation A_5 [%]	A_{80} [%]
Rolled condition*	Ø 910	min. 11	–
GKZ annealed	max. 640	min. 22	min. 18

* Restricted mechanical property ranges can be agreed on request.

General thickness tolerances

Strip thickness [mm]	1.5–2.54	2.55–4.03	4.04–6.03	6.04–8.03	8.04–9.03	9.04–11.03	11.04–14.03	14.04–16.00
Standard tolerances [mm]	± 0.04	± 0.04	± 0.05	± 0.055	± 0.06	± 0.07	± 0.08	± 0.10
Special tolerances [mm]	± 0.03	± 0.035	± 0.04	± 0.045	± 0.05	± 0.055	± 0.06	± 0.07

Possible delivery options


Options	Mill edge (NK) Cut edge (GK)	pickled		slit	trimmed	cut to length	annealed	not annealed
		pickled	unpickled					
C67/C67S	NK or GK	✓	or ✓	✓	✓	✓	✓	✓

General delivery options

Coil inner diameter:	standard 508 mm / optional 610 mm
Coil outer diameter:	max. 1,890 mm
Coil weight:	max. 20.5 kg/mm strip width
Strip width:	max. 720 mm
Strip thickness:	1.5 – 16 mm

Please contact our sales/technical customer advice team for detailed information.

Application examples for heat treatable and spring steel



Special mill grades feature unique thyssenkrupp properties. Other terms and conditions of supply not specified here will be based on the applicable specifications. The specifications used will be those valid on the date of publication of this product information.

General information

All statements as to the properties or utilization of materials and products are for the purposes of description only. Guarantees in respect of the existence of certain properties or utilization are only valid if agreed in writing. Subject to technical changes. Reprints, in whole or in part, only with the permission of thyssenkrupp Hohenlimburg GmbH. The latest version of this product information can be found at: <https://www.thyssenkrupp-steel.com/en/publications.html>