

# Cold-rolled steels for enameling



Issue: October 2016, version 0

## Brief profile

Cold-rolled steel sheet for enameling is made from either mild unalloyed deep-drawing steel or IF (interstitial free) steel. thyssenkrupp offers various grades for conventional enameling (EK) and direct enameling (ED). Depending on the grade they are suitable for simple to complex forming operations and display good enamelability.

In addition to the DC01EK, DC04EK, DC06EK, DC03ED, and DC04ED grades described in the DIN EN 10209 standard, thyssenkrupp offers the special mill grade DC06EK Plus. The DC04EK and DC06EK grades are also available with superior forming characteristics (r and n values).

Whereas the DC01EK, DC04EK, DC03ED, and DC04ED grades are suitable for the production of simple shapes such as flat shower trays, baking trays, and side walls for white goods, the DC06EK and DC06EK Plus grades are designed especially for more challenging forming operations and allow the production of more complex geometries.

---

## Content

01	Brief profile
02	Available steel grades
02	Surface finish and average roughness values
03	Technical features
04	Available dimensions
07	Sample applications

---

## Available steel grades

Steel grade	Standard designation as per DIN EN 10209
● DC03ED	DC03ED
● DC04ED	DC04ED
● DC01EK	DC01EK
● DC04EK	DC04EK
● DC06EK	DC06EK
● DC06EK Plus	Special mill grade

## Surface finish and average roughness values

Cold-rolled mild steel products for enameling are supplied in finishes A and B in accordance with DIN EN 10130 and in smooth or matte finishes as per DIN EN 10209. Other average roughness value ranges are possible subject to agreement.

### Surface finish and average roughness value

Surface finish	Indicator	Average roughness values $R_a$ [ $\mu\text{m}$ ]
Matte	m	$0.60 < R_a \leq 1.90$
Rough	r	$R_a > 1.6$

## Technical features

### Engineering properties <sup>1)</sup>

Test direction transverse to rolling direction	Thickness t [mm]	Yield strength R <sub>e</sub> [MPa]	Tensile strength R <sub>m</sub> [MPa]	Elongation A <sub>80</sub> min. [%]	Vertical anisotropy <sup>2)</sup> r <sub>90</sub> min.	Strain-hardening exponent <sup>2)</sup> n <sub>90</sub> min.
<b>To DIN EN 10209</b>						
Steel grade						
● DC03ED	0.7–2.0	140–240	270–370	34	–	–
● DC04ED	0.7–2.0	140–210	270–350	38	–	–
● DC01EK	0.7–2.0	140–270	270–390	30	–	–
● DC04EK	0.7–2.0	140–220	270–350	36	1.3	0.18
	0.7–2.0	120–190	270–330	38	2.0	0.19
● DC06EK	2.0–2.5	120–190	270–330	38	1.6	0.19
	≥2.5	120–190	270–330	38	1.4	0.19
	0.7–2.0	100–170	270–330	40	2.0	0.20
● DC06EK Plus <sup>3)</sup>	2.0–2.5	100–170	270–330	40	1.6	0.20
	≥2.5	100–170	270–330	40	1.4	0.20

Unless stated otherwise, the values apply to thicknesses from 0.7–2.0 mm and for a period of 6 months from the date the products are made available. Refer to the applicable EN standards for supplements and deductions for other thicknesses. Restricted engineering properties are possible at extra cost and subject to agreement.

● Cold-rolled strip

<sup>1)</sup> The values apply to the cold re-rolled condition.

<sup>2)</sup> Improved forming characteristics compared to standard.

<sup>3)</sup> Special mill grade.

### Chemical composition

Mass fractions in ladle analysis	C [%] max.	Mn [%] max.	P [%] max.	S [%] max.	Ti [%] max.
<b>To DIN EN 10209</b>					
Steel grade					
● DC03ED	<sup>1)</sup>	0.40	0.035	0.050	–
● DC04ED	<sup>1)</sup>	0.40	0.030	0.050	–
● DC01EK	0.08	0.60	0.045	0.050	–
● DC04EK	0.08	0.50	0.030	0.050	–
● DC06EK	0.02	0.50	0.020	0.050	0.20
● DC06EK Plus <sup>2)</sup>	0.02	0.50	0.020	0.050	0.20


● Cold-rolled strip

<sup>1)</sup> The steel grade can usually be decarburized in the solid or molten phase. Following decarburization the carbon content may be max. 0.004% in the product analysis.


<sup>2)</sup> Special mill grade.

## Available dimensions


DC03ED, DC04ED



DC01EK, DC04EK



### DC06EK, DC06EK Plus



## Sample applications



Bathtubs.



Baking trays.

Special mill grades are supplied subject to the special conditions of thyssenkrupp. Other delivery conditions not specified here will be based on the applicable specifications. The specifications used will be those valid on the date of issue of this product information brochure.

### General information

All statements as to the properties or uses of materials or products are for descriptive purposes only. Guarantees in respect of specific properties or uses are only valid if agreed in writing. Subject to technical changes. Reprints, even extracts, only with permission of thyssenkrupp Steel Europe AG. The latest version of the product information brochure can be found at: [www.thyssenkrupp-steel.com/publications](http://www.thyssenkrupp-steel.com/publications)